

Adore























Adore

Meet Adore, a Textaafoam Original. An 'adorable' knitted velvet from our Comfort Collection, suitable for all kinds of upholstery. This collection stands for softness, volume and elegance.

Adore is piece dyed with a printed slub-effect. A tone-in-tone backing provides an extra luxurious look. Easy to clean, soft and machine washable at 30 degrees Celsius, this article has proofed itself as a real crowdpleaser.

Introduced in 2017, it still is a major success all over Europe. Now available in broad range of contemporary colours from stock. Packed with care in suspended boxes for full rolls or bubblewrap for exact meters to avoid lasting pressure marks during storage and transport.

Adore is unique Adore is easy to clean Adore is washable Adore is the original

- Please note that no fluor-carbon treatment has been used for this quality, due to the production and dyeing method it is automatically damp & dirt prevented, stain resistant and easy to clean & maintain.
- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

Textaafoam originals Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.

Composition

/ faceside 100%PES / backside 100%PES / knitted velvet

Suitable for



Please note: colours may vary according to your screen settings.



Please note: colours may vary according to your screen settings.



Adore - Article passport

Adore is a piece dyed knitted velvet with a printed slub-effect.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics					
Productgroup	knitted velvet				
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery				
Composition faceside	100%PES				
Composition backside	100%PES				
Bonding	woven				
Statistic code	60053700				
Dyeing method	piece dyed				
Available colours	32				
Packaging	hoxes				

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09		
				Dry	Wet	DGM	DGM+			
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	88.000		min. 20.000	min. 40.000	А		
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	5		min. 3-4	min. 4	А		
Colour fastness to light	DIN EN ISO 105-B02:2014-11. Process 3, exposure level 5									
	light colours	CTL	grade	5		min. 4	min.5	В		
	middle colours	CTL	grade	5		min. 4	min.5	В		
	dark colours	CTL	grade	le 4-5		min. 4	min.5	B-C		
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11									
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A		
	middle colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A		
	dark colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A		
gnitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	СТL		passed						

			1				1	
Processing specifications								
Minimum workable width in centimeters	± 138							
Roll length in meters	± 35							
Material weight in grams per linear meter	± 580							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	691	583	min. 350	min. 400	A/B
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	71,7	61,4	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,5	2,0	max. 5	max. 4	A/A
Delamination	DIN 53530:1081-02	CTI	Newton	20.2	20.5	n/a	n/a	n/a

Cleaning specifications	•	•						
Test	Test specification	Executed by laboratory:	Unit	Test	result	Norm RAL GZ 430/4:2019		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-0,4	0,0	n/a	n/a	A/A
	- We recommend to wash the cover	inside out and immediat	ely place the co	over back to the pie	ce of furniture, sligh	itly damp, after was	hing.	•

Centexbe

Centexbel



Chemical substances











REACH

Oeko-Tex, product class II







passed

certified











creativity in fabrics

Textaafoam b.v.La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands