



Champ





Champ

Meet our Champ! This polyester blended textile is a radiant addition to our Comfort Collection. A collection that consists only of soft, voluminous and elegant fabrics.

Luxury and elegance, that is what Champ expresses. This fine woven quality of 95% virgin polyester and 5% nylon has the look and feel of a true velvet. It's soft and shiny with a subtle cloudy effect.

The developed colour range of natural and grey tones, supplemented with a full range of warm and deep colours, will make your choice of furniture radiate in style.

Champ will continue to be a champ, thanks to the applied moisture and dirt treatment. Woven on an airjet-loom, piece dyed and an excellent performance on all technical chemical and practical upholstery tests. It's also machine-washable at 30 degrees*

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.
- Please note that during washing the damp- and dirt prevented treatment will disappear faster.
- Dirt and damp prevention treatment applied.

Textafoam originals Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.

Composition

/ faceside 95%PES 5%NY
/ backside 100%PES
/ chenille flatweave

Suitable for


sofa's, beds, chairs with fitted and loose fitting upholstery



blackberry 177



curry 216




grey 65



hazel 96



hunter 156



ivory 101



lightgrey 60



liver 10



navy 49



ocre 23



onyx 169



pale 200

Please note: colours may vary according to your screen settings.



pine 199



sage 203



scarlet 141



shell 196



thyme 206



wood 108

Please note: colours may vary according to your screen settings.

Champ - Article passport


A soft and shiny fine woven fabric with a subtle cloudy effect.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	chenille flatweave	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	95%PES 5%NY	
Composition backside	100%PES	
Bonding	non-woven	
Statistic code	54075200	
Dyeing method	piece dyed	
Available colours	18	
Packaging	transparent plastic	






Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 20.000	min. 40.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-B02:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
	dark colours	CTL	grade	4		min. 4	min.5	C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	B/A
Ignitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 143							
Roll length in meters	± 40							
Material weight in grams per linear meter	± 508							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.063	616	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	64,4	38,7	min. 25	min. 30	A/B
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,0	1,6	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	29,2	28,3	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	0,0	0,0	n/a	n/a	A/A
    		<p>- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.</p> <p>- Please note that during washing the damp- and dirt prevented treatment will disappear faster.</p> <p>- Dirt and damp prevention treatment applied.</p>						



Textaafoam

creativity in fabrics

Textaafoam b.v.

La Défense 11 | 5026 SC Tilburg

P.O. Box 12 | 5050 AA Goirle

The Netherlands

T +31(0)13 534 5934

F +31(0)13 534 7586

E info@textaafoam.nl

www.textaafoam.nl