



Dream





Dream

Did you ever wish for commercial fabric, easy going, strong on performance, nicely priced and sustainable as well? Welcome to a dream come true.

Our upholstery fabric Dream is a promising element of our sustainable www.fabraa.com collection.

This sustainable fabric is piece dyed, woven on an air jet loom and made of 100% recycled polyester. The subtle structure of the combined shiny and dull yarns, gives just that slightly sparkly effect, which creates a wow-experience. It's definitely a must-have for your collection. To convince you even further, the touch is soft and comfortable and the full range of colors, will ensure that your new favorite will be there as well. The non-woven backing is also made from 100% RPET, to give extra stability and volume to this fabric.

Polyester fabrics are easy to clean by itself, but if necessary it is also machine-washable at 30 degrees Celsius.

Open your eyes and be amazed by our Dream.

- This article has been tested practical, chemical and technical, if during use as certain hairiness appears, please note that it can easily be taken away with a pilling machine.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

Fabraa Upholstery fabrics with a conscience. We make sustainable choices easy by offering a wide range of high-quality, affordable upholstery fabrics with consideration for the conditions throughout the supply chain.

Composition

/ faceside 100%RPET


/ backside 100%RPET

/ flatweave

*R=recycled

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



ashgrey 40



blush 92



brown 15



carmine 36



cognac 28




desert 109



darkgrey 68



hunter 156



ivory 101



linen 110



liver 10



mustard 06

Please note: colours may vary according to your screen settings.



natural 01



niagara 158




onyx 169



royalblue 47



sepia 176




slate 87



thyme 206



wood 108



zinc 167

Please note: colours may vary according to your screen settings.

Dream - Article passport

A slightly sparkly flatwoven fabric in a vivid colour range.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	100%RPET
Composition backside	100%RPET
Bonding	non-woven
Statistic code	54075200
Dyeing method	piece dyed
Available colours	21
Packaging	transparent plastic

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 12.000	min. 16.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A-B/A
dark colours	CTL	grade	4	3-4	dry: 4, wet: 3	dry: > 4, wet: 3-4	B/A	
	ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL	passed				



Processing specifications

Minimum workable width in centimeters	± 143
Roll length in meters	± 40
Material weight in grams per linear meter	± 580

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.511	1.036	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	140,5	96,6	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,0	1,6	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	39,5	12,3	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-0,6	0,0	n/a	n/a	A/A

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.



FABRAA[®]
fabrics with a conscience

Textafoam b.v.

La Défense 11 | 5026 SC Tilburg

P.O. Box 12 | 5050 AA Goirle

The Netherlands

T +31(0)13 534 5934

F +31(0)13 534 7586

E info@fabraa.com

www.fabraa.com