



Facet



Textafoam  | Performance
creativity in fabrics



Facet

Featuring in our Performance Collection: Facet. This woven fabric of recycled wool is a high performing sustainable fabric.

The Performance Collection only brings fabrics that meet the highest standards in durability and maintenance making them long lasting and suitable for almost every type of upholstery.

Due to its composition Facet passes the BS5852 cigarette (part 0) & match (part 1) and also the EN1021 cigarette (part 1) & match (part 2).

Facet consists of 100% recycled woollen yarns, carded from regenerated post-consumer wool like clothing and other products. Carding is an environmental friendly and highly specialized way of producing. It enables us to give woollen articles a second life.

Facet has a light melange aspect that makes it stand out from virgin woollen qualities. This article comes in a wide and contemporary colour line to match all your creative needs. Facet may be used to upholster many different types of furniture and is also very suitable for drapery. Now available from stock.

Textafoam^{originals} Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.

Composition

/ Faceside 75%WO 25%PA

/ Flatweave

Suitable for


Sofa's, beds, chairs with fitted and loose fitting upholstery, drapery



zwart 1003



fuchsia 77



anthracite 67



prune 76



navy 1007



middengrijs 1001



purple 78



blue 45



azure 144




lightgrey 1000



aubergine 74



petrol 56



ashgrey 40



natural 01




mint 50



beige 1037



olive 53



pink 73



kiezel 7



shitake 124



army 14



blossom 166



dolphin 180



taupe 1008



darkbrown 18



terra 31



rust 29



pistachio 52



maize 22



aqua 143



yellow 24



lightblue 41



oceanblue 147



orange 2012/b



indigo 90



red 2011



mandarin 129



nightshade 178



fire 139



violet 72

Facet - Article passport

Woolly fabric with a soft grip. Made from recycled material.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery, drapery
Composition faceside	75%WO 25%PA
Statistic Code	51113080
Dyeing method	yarn dyed
Available colours	40

Durability specifications

Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				DRY	WET	DGM	DGM+	
Abrasion Resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 12.000	min. 16.000	A
Pilling	DIN EN ISO 12945-2:2000-11, 2000 cycles	CTL	grade	3-4		min. 3-4	min. 4	C
Colour fastness to light	DIN EN ISO 105-B02:2014-11, Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min. 5	B
	middle colours	CTL	grade	5		min. 4	min. 5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: min 4, wet: 3-4	A/A
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) Regulations: 1988 No. 1324, Schedule 4 part I, Ignition source 0: cigarette							
		Centexbel		passed				
Ignitability (match test)	DIN EN ISO 1021-1:2014, Source: Smouldering cigarette							
		Centexbel		passed				
Ignitability (match test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) Regulations: 1988 No. 1324, Schedule 4 part I, Ignition source 1: Match flame equivalent							
		Centexbel		passed				

Processing specifications

Minimum workable width in centimeters	± 145
Roll length in meters	± 50
Material weight in grams per linear meter	± 600

Test	Test Specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2016-01		Norm DIN EN 14 465:2006-09
				WARP	WEFT	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	455	348	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	40,5	35,2	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07, Load 180 N	CTL	mm	2,7	2,7	max. 5	max. 4	A/A
Chemical substances	REACH	Centexbel		passed				

Cleaning specifications



Textaafoam
creativity in fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl