



Rate



OEKO-TEX®
CONFIDENCE IN TEXTILES



Textaafoam  | Timeless
creativity in fabrics



Rate

Rate is a flatwoven quality, which is in the Textaafoam Timeless Collection. This collection represents all of our creative essentials.

Fabrics that offer the best value for money and suit every style all year round. With Rate we developed a slightly rough constructed fabric with a light bicolour aspect. Laminated with a non-woven backing, Rate feels extra soft and voluminous.

Rate consists of a polyester yarn, woven on an air jet loom. Piece dyed and treated to be moisture and dirt repellent. Washable at 30 degrees (machine wash)*.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.
- Please note that washing has a negative effect on the damp- and dirt prevented treatment, by washing the treatment will disappear faster.
- Dirt and damp prevention treatment applied.

***Textaafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 100%PES
/ backside 100%PES
/ polyester flatweave

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



ashgrey 40



blush 92




bronze 116



denim 153



desert 109



darkgrey 68



hazel 96



hunter 156




liver 10



mustard 06




natural 01



niagara 158


Please note: colours may vary according to your screen settings.



onyx 169



pearl 106



scarlet 141




sepia 176



thyme 206



wood 108



zinc 167

Please note: colours may vary according to your screen settings.

Rate - Article passport


Fabric with a light multi-coloured aspect and a soft and full hand feel.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	polyester flatweave	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	100%PES	
Composition backside	100%PES	
Bonding	non-woven	
Statistic code	54075200	
Dyeing method	piece dyed	
Available colours	19	
Packaging	transparent plastic	

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	>100.000		min. 8.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	4		min. 4	min.5	C
	middle colours	CTL	grade	4		min. 4	min.5	C
	dark colours	CTL	grade	4-5		min. 4	min.5	B-C
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	3-4	3	dry: 4, wet: 3	dry: > 4, wet: 3-4	C/B
gnitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 143							
Roll length in meters	± 45							
Material weight in grams per linear meter	± 522							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.519	631	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	141,8	50,5	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,0	2,0	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	34,7	19,3	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-0,8	0,0	n/a	n/a	A/A



- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.
- Please note that washing has a negative effect on the damp- and dirt prevented treatment, by washing the treatment will disappear faster.
- Dirt and damp prevention treatment applied.



Textaafoam
creativity in fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl