

Tundra





























Tundra

Featuring in our Performance Collection: Tundra. This flatwoven quality with a light mélange consists of 100% polyester Trevira yarns.

The Performance Collection only brings fabrics that meet the highest standards in durability and maintenance making them long lasting and suitable for almost every type of upholstery.

Due to its composition Tundra passes the BS5852 cigarette (ignition source 0), match (ignition source 1) & Crib 5 (ignition source 5) as well as the EN1021 cigarette (part 1) & match (part 2).

Tundra consists of 100% polyester Trevira yarns and is piece dyed. While durable and strong, a special finish provides its wonderful light woolly appearance. This makes Tundra suitable for drapery as well as all kinds of upholstery.

This article comes in a wide and contemporary colour line of 22 colours to match all your creative needs. All available from stock.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.

Textaafoam originals Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.

Composition

/ faceside 100%PES TREVIRA CS / backside n/a / flatweave

Suitable for



Please note: colours may vary according to your screen settings.



wood 108 (fr)

Tundra - Article passport Flatwoven quality with a light mélange effect. Available from stock in a wide range of contemporary and commercial colours. **Product characteristics** Productgroup flatweave sofa's, beds, chairs with fitted and loose fitting upholstery Applications Composition faceside 100%PES TREVIRA CS Composition backside n/a Bonding / Coating n/a Statistic code 54075200

piece dyed

transparent plastic

22

Durability specifications										
Test		Test specification	Executed by Unit laboratory:		Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09	
					Dry	Wet	DGM	DGM+		
Abrasion resistance - yarn breakage		DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	75.000		min. 12.000	min. 16.000	А	
Pilling		DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	Α	
Colour fastness to light		DIN EN ISO 105-B02:2014-11. Process 3, exposure level 5								
		light colours	CTL	grade		5	min. 4	min.5	В	
		middle colours	CTL	grade		5	min. 4	min.5	В	
		dark colours	CTL	grade	5		min. 4	min.5	В	
Colour fastness to rubbing		DIN EN ISO 105-X12:2016-11								
		light colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A	
		middle colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A	
		dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A	
gnitability (cigarette test)		BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	Trevira CS Trevira CS		passed					
		DIN EN ISO 1021-2:2014. Source: smouldering cigarette			passed					
gnitability (match test)		BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 1: match flame equivalant	Trevira CS Trevira CS		passed					
		DIN EN ISO 1021-2:2014. Source: match flame equivalent			passed					
Ignitability (crib)	Crib 5	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) Regulations: 1988 No. 1324. Schedule 4 part I. Ignition source 5: Crib 5	Trevira CS		passed					

Processing specifications								
Minimum workable width in centimeters	± 141							
Roll length in meters	± 50							
Material weight in grams per linear meter	± 515							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.615	650	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	97,8	63,4	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,0	2,0	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed			•	•
	Oeko-Tex, product class II	Centexbel		certified		1		

Cleaning specifications									
Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09		
			Warp	Weft	DGM	DGM+			
DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-0,8	0,0	n/a	n/a	A/A		
	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02,	laboratory:	laboratory:	laboratory:					



Dyeing method

Available colours

Packaging













OEKO-TEX®



















Textaafoam b.v.La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934 F +31(0)13 534 7586 E info@textaafoam.nl www.textaafoam.nl

aug 2021