



Unique



Textaafoam  | Comfort
creativity in fabrics



Unique

Meet Unique, a heavy woven velvet with a very soft and full handfeel in our Comfort Collection. A collection that stands for softness, volume and elegance. Perfect for all kinds of upholstery as well as drapery.

Unique is a quality that combines cotton and polyester, making it possible to create beautiful soft and elegant contemporary colours. Piece dyed with a matt, naturel and light blended vintage aspect.

Washable and easy to clean, available from stock in various colours it is hard not to like this article. Packed with care in suspended boxes for full rolls or bubblewrap for exact meters to avoid lasting pressure marks during storage and transport.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.

***Textafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition


/ faceside 67%PES 33%CO
/ backside n/a
/ polyester cotton velvet woven

Suitable for


sofa's, beds, chairs with fitted and loose fitting upholstery




apple 157




azure 144




blossom 166



blush 92




cacao 83



cappuccino 11




carmine 36




desert 109



ecru 102



eucalyptus 193




grey 65



iceblue 43


Please note: colours may vary according to your screen settings.



indigo 90




liver 10




magnolia 160




mauve 140




mint 50



mustard 06




natural 01




petrol 56




shell 196



shitake 124




stone 181




sun 133

Please note: colours may vary according to your screen settings.



turquoise 44



zinc 167

Please note: colours may vary according to your screen settings.

Unique - Article passport


A heavy woven velvet with a very soft and full handfeel with a matt, naturel and light blended vintage aspect.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	polyester cotton velvet woven	
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery	
Composition faceside	67%PES 33%CO	
Composition backside	n/a	
Bonding / Coating	n/a	
Statistic code	58013700	
Dyeing method	piece dyed	
Available colours	26	
Packaging	boxes	

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	70.000		min. 20.000	min. 40.000	A
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	A
	middle colours	CTL	grade	5		min. 4	min.5	A
	dark colours	CTL	grade	5		min. 4	min.5	A
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	4-5	4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	4-5	4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	dark colours	CTL	grade	4-5	4	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	 BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 138							
Roll length in meters	± 35							
Material weight in grams per linear meter	± 600							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.317	867	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	65,0	34,0	min. 25	min. 30	A/B
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	3,4	2,7	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	n/a	n/a	n/a	n/a	n/a
Chemical substances	REACH	Centexbel	passed					
	Oeko-Tex, product class II	Centexbel	certified					

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	0,0	0,0	n/a	n/a	A/A



- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture slightly damp after washing.

