



Soda





Soda

A polyester flatwoven textile which is in the Textafoam Timeless Collection. This collection represents all of our creative essentials and offer the best value for money.

With Soda, our product development team created a simple, elegant, new upholstery textile with a light mélange aspect. Strong, durable, and laminated with a non-woven backing, therefore it feels also comfortable and voluminous.

Soda is a 100% virgin polyester textile, woven on an air jet loom. Piece dyed and available in a wide, trendy, and modern colour-line, suitable for all types of furniture, buttoned, tight fitted and also perfect for loose fitting upholstery, as it is machine-washable at 30 degrees Celsius*.

During use a light woolly or hairy aspect may appear, this has no further influence on the durability of this textile and can easily be taken away with a pilling machine.

You can drink a soda.... but try it as an upholstery textile and you will be amazed.

- Always be careful with sharp or rough objects such as watches, buckles, or velcro, as they may damage the fabric.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.

***Textafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition

/ faceside 100%PES
/ backside 100%PES
/ chenille flatweave

Suitable for

sofa's, beds, chairs with fitted and loose fitting upholstery



ashgrey 40



beige 05



blush 92



brass 170



cacao 83



charcoal 79



cognac 28




denim 153



ecru 102



forest 162



grey 65



hazel 96

Please note: colours may vary according to your screen settings.



herb 214



ivory 101




liver 10



natural 01



taupe 12



zinc 167

Please note: colours may vary according to your screen settings.

Soda - Article passport

A simple and elegant upholstery textile with a light mélange aspect.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	chenille flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	100%PES
Composition backside	100%PES
Bonding	non-woven
Statistic code	54075200
Dyeing method	piece dyed
Available colours	18
Packaging	transparent plastic

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	80.000		min. 12.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4-5		min. 3-4	min. 4	A
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	5		min. 4	min.5	B
	middle colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	dark colours	CTL	grade	4-5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL		passed				

Processing specifications

Minimum workable width in centimeters	± 138
Roll length in meters	± 50
Material weight in grams per linear meter	± 450

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	860	753	min. 350	min. 400	A/A
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	122,3	136,6	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,0	2,5	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	39,2	54,2	n/a	n/a	n/a
Chemical substances	REACH	Centexbel		passed				
	Oeko-Tex, product class II	Centexbel		certified				

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	-0,4	0,0	n/a	n/a	A/A

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.



Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl